YUUNNAN YUNYE ROSIN Co., LTD.



LONGCHUAN TOWN NANHUA COUNTY CHUXIONG YUNNAN

TEL: 0878-7222798

Product Technical Data Sheet

DPR

Product name

Disproportionated Rosin

Manufacturer

YUNAN YUNYE ROSIN CO.,LTD.

Product description

The DPR is derived from gum rosin which is dehydrogenated and hydrogenated by catalyst. For its pale color and superior oxidation resistance properties, the DPR is widely used in ABS resin, synthetic rubber emulsifier, water soluble pressures sentitive adhesive (WSPSA) etc.

Typical Properties

| Property | | X Grade |
|----------------------------------|--------|--------------|
| LovibondColor | Yellow | ≤20 |
| | Red | ≤2.1 |
| Color | | n or lighter |
| Ring and Ball Softening Point °C | | ≥7.5 |
| Acid Number(mg KOH/g) | | 150-160 |
| Abietic Acid (%) | | ≤0.5 |
| Dehydroabietic Acid(%) | | ≥48 |
| Unsaponificable matter | | 9 13% |

Note: YunNan Yunye Roisn Co, Ltd. shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the seller's conditions of sales. The more detailed technical information will be given by us.

Packing

225KGS net weight in galvanized iron drum

Precautions

Keep away from heat source or ignition source in transportation or storage, prevent from sunshine and rain, and cannot store together with corrosive article

The product that is crashed and packed in paper bag should avoid being stored in the condition of the temperature above 35°C in order to prevent lumping